PRELIMINARY AMENDMENT

U.S. Appln. No.: 10/516,708 Atty. Docket No.: Q85154

AMENDMENTS TO THE SPECIFICATION

A substitute specification is submitted herewith, both a clean copy of the specification and a copy showing the changes are provided.

The undersigned certifies that no new matter is included in the substitute specification.

Please delete the present Abstract of the Disclosure.

Please add the following new Abstract of the Disclosure:

ABSTRACT OF THE DISCLOSURE

remainder of tin when the alloys are melted in mixture.

The solder contains Sn-Zn alloy(s) having a single composition ratio or a plurality of composition ratios, and Sn-Bi-Ag alloy(s) having a single composition ratio or a plurality of composition ratios. The solder includes zinc at 7 to 10 weight % both inclusive, bismuth at 0.001 to 6 weight % both inclusive, silver at 0.001 to 0.1 weight % both inclusive, and the

3